



IMPLANTABLE JOINT PROSTHESIS

This application claims benefit under 35 U.S.C. § 119(e) of Provisional U.S.

Serial No. 60/223,863, filed 8 August 2000, and entitled INSTRUMENTATION AND METHOD FOR IMPLANTING A PROSTHETIC INTERVERTEBRAL BODY and of Provisional U.S. Serial No. 60/265,218 entitled GRAVITY ASSISTED LOCALIZATION SYSTEM, filed January 31, 2001 under Express Mail Label Number EL674301928US.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The invention relates to implantable prostheses that are suitable for replacement of diarthroidal or arthroidal joints by creating an artificial diarthroidal-like joint at the site of the implant.

In a particular embodiment, the invention relates to implantable prostheses serving as replacements for at least a portion of the intervertebral disc material, i.e., a spinal disc endoprosthesis suitable for implantation in vertebrates, including humans.

2. Description of Related Art

Many joints in the human body, such as hips, knees, shoulders, etc., are diarthroidal, meaning that the joints include a joint capsule that is filled with fluid. The capsule fluid lubricates the joint, and allows the surfaces of the joint to move with a low coefficient of friction. The spine, by contrast, can be considered to be a series of joints, some of which (the anterior joint or disc) lack a fluid filled capsule and are therefore arthroidal (the spine also contains facet joints that are diarthroidal). The interior portion of intervertebral discs are not provided by the body with significant blood supply; their homeostasis is enhanced by the diffusion of fluids into the disc tissue, thus supplying them with nutrients. This, to some extent, allows the tissue to

grow and repair damage done by stress as the joint moves. Despite this process in mature adults, spinal disc tissue degrades continuously over time. Sufficiently advanced degeneration can lead to herniation or rupture of the spinal disc.

Herniation of a spinal disc can result in a number of debilitating symptoms, including intractable pain, weakness, and sensory loss. Treatment of these symptoms frequently requires surgical removal of at least a portion of the herniated disc, a procedure known as discectomy. Often discectomy alone cannot stop the progressive degeneration at the level of disc excision. An additional procedure is often performed in conjunction with the discectomy with the objective of fusing together (arthrodesis) the vertebral bodies surrounding the affected disc space. This is accomplished by removing the cartilaginous endplates by scraping the surfaces of the vertebral body and inserting a piece of graft bone, which may be an allograft from a bone bank, or an autograft, typically taken from the iliac crest of the patient, or other suitable material..

The discectomy and arthrodesis procedures can be problematic, however. Discectomy problems have been described above. The grafting or fusion procedure has a variable success rate of about 80% , and even when successful, requires considerable recovery time before fusion is complete. Perhaps of even greater concern, successful fusion eliminates normal spinal biomechanics. Range of motion at the level of the fusion is ideally eliminated, because the affected vertebrae have been effectively joined to form a single bone. Because the patient tries to maintain the same overall range of motion of the entire spine, additional stress is imposed on the intervertebral discs of the adjacent vertebrae . This, in turn, may lead to accelerated degeneration at levels above and below the fusion site, which may require additional treatment, including discectomy and fusion. Grafting procedures carry

recovery time, and reduce the occurrence of postoperative degeneration at levels above and below the implant, as compared with fusion techniques. In addition, such an implant would avoid the need for harvesting of autograft bone tissue, thereby eliminating morbidity at the harvesting site. Such an implant should also provide elasticity and damping sufficient to absorb shocks and stresses imposed on it in a manner similar to that of the natural spinal disc.

SUMMARY OF THE INVENTION

This invention satisfies the needs and concerns described above. Other concerns can arise that are more unique to any joint replacement or reconstruction, particularly with respect to device stability, range of motion, and postoperative material degradation. In general, in patients undergoing joint replacement, the patient's condition and quality of life is improved more by a technique that provides a range of motion that more closely approximates the range of motion of a healthy joint (assuming that this can be done in a safe manner) than by a technique that provides a decreased range of motion. Important parts of accomplishing this goal include using an implant design that is highly stable when implanted, and making use of the soft tissue associated with the joint (to the extent possible) to stabilize the implant and leave restriction of some of the motion of the joint to the soft tissue. This allows the implant design to be considerably simpler. Irrespective of the joint being implanted, an implant that provides an effectively sealed, fluid filled capsule (i.e., an artificial diarthroidal-like joint) will likely provide an added margin of safety because the moving surfaces are isolated from the surrounding tissue and body fluids, and the environment in which the moving surfaces operate can be engineered and controlled. The lubrication effects in such a joint allow it to function more effectively and potentially generate less wear debris. Any wear debris that is generated, however, is

09924258 032202

surfaces and the prepared surfaces of the bone cooperate to contain the implant between the bone surfaces. The smooth inner surfaces of the rigid opposing plates or shells are shaped to cooperate and articulate with the shape of the smooth surface of the deformable resilient central body to allow relatively unconstrained motion of the plates or shells with respect to the resilient central body until the limit of acceptable motion is reached. Once the limit of allowable motion is reached, the shape of the inner surface of the plate or shell cooperates with the shape of the deformable resilient central body to effectively resist any movement beyond the desired motion. This allows the motion of a joint containing the implant to closely approximate the motion provided in a healthy joint, alleviating undesirable stresses imposed on the joint or bone structure, or in the case of a vertebral implant, on adjacent joints as well. This, in turn, reduces the likelihood of further joint degeneration in adjacent joints.

The deformable resilient central body also provides elasticity and dampening properties, similar to those provided by healthy joint tissue. It is also sufficiently creep-resistant or resistant to plastic deformation to avoid post-operative loss of disc space height and to maintain appropriate joint geometry. The surface of the central body is hard, in some embodiments harder than the interior, which provides good wear resistance. It is also very lubricious, which provides good tribological properties in conjunction with the inner surfaces of the rigid plates or shells.

The resulting implant is safe because it can be implanted with precision, and once implanted, it is stable. It is extremely effective because the geometry of the internal surfaces is configured to provide a range of motion that closely approximates that provided by healthy joint tissue, thus allowing coordinated movement of the spine and reducing stress on adjacent joints.

00000000.000000

In another aspect, the invention relates to an implant that effectively provides an artificial diarthroidal-like joint, suitable for use in replacing any joint, but particularly suitable for use as an intervertebral disc endoprosthesis. In this aspect, the implant contains, in addition to the opposing rigid plates or shells and deformable, resilient central body described above, a flexible sleeve or sheath that extends between edges of the opposing plates or shells.

The inner surface of this sheath, together with the inner surfaces of the rigid plates or shells, defines a cavity surrounding the central body. Most, if not all, of the interior space of this cavity can be filled with a fluid lubricant, further decreasing the frictional force between inner surfaces of the plates or shell and the surface of the central body, again within the constraints of allowable motion.

The flexible sleeve or sheath serves to hold the implant together as a single unit, making it easier to manipulate during the implant procedure. It also retains the lubricant within the implant and provides a contained, sealed environment that keeps tissue from entering the interior of the implant, isolates the central body from possible attack or degradation by body fluids, and prevents any wear debris that might be generated from exiting the implant and migrating into surrounding tissues. The implant therefore provides a sealed capsule presenting only biocompatible surfaces to surrounding tissues, and keeping wear surfaces internal to the implant and permanently lubricated. The result is an implant with extremely good durability, because the articulating surfaces have been isolated away from the natural bone surfaces and placed in a lubricated capsule.

In yet another aspect, the invention provides a vertebral endoprosthesis, having:

0597 *Phyllanthus* **0608** *Phyllanthus*

an axial post extending toward the opposing shell; and

a circumferential groove adapted to receive a retaining ring;

a first ridge circumscribing the contact area of the inner concave surface and extending axially toward the opposing shell;

an insertion tab extending axially away from the opposing shell, and comprising an opening adapted to releasably engage a tool for manipulating, inserting, or removing the endoprosthesis;

a closable passage between the outer surface and the inner surface of the shell;

a deformable, resilient central body disposed between the inner, smooth concave surfaces of the upper and lower shells, comprising:

smooth convex upper and lower surfaces complementary and adjacent to the smooth contact area of the inner surfaces of the respective upper and lower shells;

a second ridge circumscribing each of the smooth convex upper and lower surfaces and adapted to contact the first ridge of the adjacent shell and limit the relative motion of the shell with respect to the central body;

cannot migrate and come into contact with nerves or blood vessels, and so that the desired bony ingrowth can occur. The convex outer surface also provides additional surface area that contacts cancellous bone, increasing both the opportunity for bony ingrowth and the frictional force holding the shells in place. The mating of the concave inner surfaces of the shells with the curved shape of the central body provides a simple ball-and-socket-like system that is inherently highly stable under compression, as it will be when implanted. The embodiment of the invention using concavo-convex shells and a convex surface on the deformable central body therefore provides immediate mechanical stability.

Because the range of motion provided by the implant closely approximates that of a healthy disc, post-operative adjacent level disc degeneration is minimized or avoided entirely. In addition, the implant does not significantly constrain joint torsion, but instead relies on the remaining soft tissue (e.g., remaining disc annulus, ligaments, etc.) in and around the implanted joint to provide appropriate torsional constraint. Neither the shapes of the plates or shells or of the central body, or of the central retaining posts or central axial opening restrict the torsional movement of the shells relative to the central body (i.e., the rotation of the shells or of the central body about a central axis. This is of benefit because it significantly decreases the stress imposed on the interface between the bone surfaces and the outer surfaces of the implant, making movement of these implant surfaces relative to the bone less likely. This, in turn, increases the likelihood of bony ingrowth instead of fibrous tissue formation, and therefore increases long-term stability.

BRIEF DESCRIPTION OF DRAWINGS

The invention can be more clearly understood by reference to the following drawings, which illustrate specific embodiments thereof, and which are not intended to limit the scope of the appended claims.

FIG. 1 is a perspective drawing of an intervertebral endoprosthesis in accordance with a specific embodiment of the invention.

FIG. 2 is an elevational view of the intervertebral endoprosthesis shown in FIG. 1.

FIG. 3 is a top plan view of the intervertebral endoprosthesis shown in FIG. 1 and 2.

FIG. 4 is an isometric cross sectional view of the intervertebral endoprosthesis shown in FIG. 1, 2, and 3.

FIG. 5 is a plan view of an implant plug and plug installation tool used to insert a plug into an intervertebral endoprosthesis.

FIG. 6 is a sectional view of the intervertebral endoprosthesis shown in FIG. 1-4.

FIG. 7 is an exploded perspective view of the intervertebral endoprosthesis shown in FIG. 1-4 and 6.

FIG. 8 is a plan view (A) and sectional view (B) of one embodiment of an intervertebral endoprosthesis of the invention undergoing lateral bending.

FIG. 9 is a plan view (A) and sectional view (B) of one embodiment of an intervertebral endoprosthesis of the invention undergoing translation.

FIG. 10 is a plan view (A) and sectional view (B) of one embodiment of an intervertebral endoprosthesis of the invention undergoing lateral bending.

FIG. 11 is a plan view (A) and sectional view (B) of one embodiment of an intervertebral endoprosthesis of the invention undergoing translation.

The invention can be more clearly understood by reference to some of its specific embodiments, described in detail below, which description is not intended to limit the scope of the claims in any way.

DETAILED DESCRIPTION OF SPECIFIC EMBODIMENTS

In broad aspect, the size and shape of the implant are substantially variable, and this variation will depend upon the joint geometry. Moreover, implants of a particular shape can be produced in a range of sizes, so that a surgeon can select the appropriate size prior to or during surgery, depending upon his assessment of the joint geometry of the patient, typically made by assessing the joint using CT, MRI, fluoroscopy, or other imaging techniques.

The rigid opposing plates or shells can be made of any rigid, biocompatible material, but are generally made of a biocompatible metal, such as stainless steel, cobalt chrome, ceramics, such as those including Al_2O_3 or ZrO_2 , or titanium alloy. ASTM F-136 titanium alloy has been found to be particularly suitable. As indicated above, the outer surface of the rigid opposing plates or shells are rough, in order to restrict motion of the shells relative to the bone surfaces that are in contact with the plates. This is particularly important in the time period just after implantation (the "acute" phase of healing), since excessive movement of the implant relative to the bone can result in the formation of fibrous tissue between the bone and the implant, rather than the bony ingrowth, which is desirable for long term implant stability (i.e., during the "chronic" phase of healing). It has been discovered that a porous coating formed from nonspherical sintered beads provides very high friction between the outer surface of the shell and the bone, as well as providing an excellent interaction

with the cancellous bone of the joint, increasing the chances of bony ingrowth. One example of a suitable nonspherical sintered bead coating is that made of pure titanium, such as ASTM F-67. The coating can be formed by vacuum sintering.

At least a portion of the inner surface of each plate or shell is smooth, and of a shape that complements and articulates with the shape of at least a portion of the central body. This smoothness and correspondence in shape provides unconstrained movement of the plate or shell relative to the central body, provided that this movement occurs within the allowable range of motion.

The structural features of the shapes of the inner surface of the plate or shell and the central body that interact to limit the movement to this allowable range will necessarily vary to some extent, based on the joint in which the implant will be used. As an example, the edge of the plate or shell can be extended toward the central body, so as to form a wall that, under shear, can contact a ridge or shoulder formed in the surface of the central body. This will allow for unconstrained motion of the plate or shell except in a direction that will bring the extension into contact with the ridge. By forming the extension around the entire edge of the shell, and by forming a ridge or shoulder that encloses a portion of the surface of the central body, translational, flexural, extensional, and lateral motion of the plate or shell relative to the central body can be constrained in all directions. Those of skill in the art will recognize that a bead or ridge at other locations on the inner surface of the plate or shell will serve a similar purpose, and that the location of this bead or ridge, as well as the ridge or stop on the central body, can be varied between implants for different joints, in order to obtain the desired range of motion for that particular joint.

The plates may be identical, which is desirable for ease of manufacture, or may be of different design (shape, size, and/or materials) to achieve different

mechanical results. For example, differing plate or shell sizes may be used to more closely tailor the implant to a patient's anatomy, or to shift the center of rotation in the cephalad or caudal direction.

In a more particular embodiment, the inner surface of the shell and the outer surface of the central body can contain complementary structures that will function as an expulsion stop, so that the central body cannot be expelled from between the opposing plates or shells when the plates or shells are at maximum range of motion in flexion/extension. Examples of such structures include a post and corresponding hole to receive the post. The hole can have a diameter sufficiently large that relative motion between the shells and central body is unconstrained within the allowable range of motion, but that will nevertheless cause the post to arrest the central body before it is expelled from the implant under extreme compression. Alternatively, the diameter of the post may be such that it limits the translational movement of the central body during normal motion of the spine by contacting the surface of the hole in the central body at the limit of the allowable range of motion for the device. The elastically deformable, resilient central body may also vary somewhat in shape, size, composition, and physical properties, depending upon the particular joint for which the implant is intended. The shape of the central body should complement that of the inner surface of the shell to allow for a range of translational, flexural, extensional, and rotational motion, and lateral bending appropriate to the particular joint being replaced. The thickness and physical properties of the central body should provide for the desired degree of elasticity or damping. Accordingly, an elastomeric material is typically used for the central body. However, the central body should be sufficiently stiff to effectively cooperate with the shell surfaces to limit motion beyond the allowable range. The surface of the central body should be sufficiently hard to

provide acceptable wear characteristics. One way to achieve this combination of properties is to prepare a central body having surface regions that are harder than the material of the central body closer to its core. The central body is therefore desirably a biocompatible elastomeric material having a hardened surface. Polyurethane-containing elastomeric copolymers, such as polycarbonate-polyurethane elastomeric copolymers and polyether-polyurethane elastomeric copolymers, generally having durometer ranging from about 80A to about 65D (based upon raw, unmolded resin) have been found to be particularly suitable for vertebral applications. If desired, these materials may be coated or impregnated with substances to increase their hardness or lubricity, or both. Examples of suitable materials are provided in more detail below.

The shape of the central body may also be designed to prevent contact between the edges of the rigid opposing shells during extreme motion of the implant. For example, a ridge or lip in the region of the central body between the shells and extending laterally can provide a buffer, preventing contact between the shells. This prevents friction and wear between the shells, thereby avoiding the production of particulates, which could cause increased wear on the internal surfaces of the implant.

In a particular embodiment, one or both of the rigid opposing shells can be provided with an opening therein, in the form of a passage between the outer and inner surfaces. When the implant is partially assembled, i.e., the deformable resilient central body has been disposed between the rigid opposing shells, and the sheath has been attached to the edges of the shells, the passage can be used to introduce liquid lubricant into the implant. The passage can then be closed off (e.g., by filling it with an appropriately sized plug), thereby providing a sealed, lubricant filled inner cavity.

Attachment of the sheath to the rigid, opposing shells can be accomplished in a variety of ways. Typically the rigid opposing shell is made from a biocompatible

metallic alloy, e.g., a titanium alloy, while the sheath is typically made from an elastomeric polymeric material, such as segmented polyurethane. Attachment of the sheath to the shell can be accomplished by providing the edge of the rigid shell with a circumferential groove (the term "circumferential" in this context does not imply any particular geometry). The groove is of a shape and depth sufficient to accept a retaining ring, typically made of a biocompatible weldable wire, such as stainless steel or titanium. The sheath can be disposed so that it overlaps the circumferential groove, and the retaining ring formed by wrapping the wire around the groove over the overlapping portion of the sheath, cutting the wire to the appropriate size, and welding the ends of the wire to form a ring. Laser welding has been found to be particularly suitable in this regard.

The invention as described above can be used as a prosthetic implant in a wide variety of joints, including hips, knees, shoulders, etc. The description below focuses on an embodiment of the invention wherein the implant is a spinal disc endoprosthesis, but similar principles apply to adapt the implant for use in other joints. Those of skill in the art will readily appreciate that the particulars of the internal geometry will likely require modification from the description below to prepare an implant for use in other joints. However, the concept of using a core body having geometric features adapted to interact with inner surfaces of opposing shells to provide relatively unconstrained movement of the respective surfaces until the allowable range of motion has been reached, and the concept of encasing these surfaces in a fluid filled capsule formed by the opposing shells and a flexible sheath, are applicable to use in any joint implant.

Reference is made below to the drawings, which shall now be used to illustrate a specific embodiment of the present invention, namely a spinal disc endoprosthesis.

As can be seen best in the exploded view shown in FIG. 7, in accordance with this preferred embodiment, the present invention includes four main components: two shells 20, 40, a central body 60, and a sheath 70. The complete assembly of the device is shown in FIGS. 4 and 6, wherein the central body 60 is bracketed between shells 20, 40. The flexible sheath 70 extends between the two opposing shells 20, 40, and encapsulates the central body 60. As described in further detail below, the geometric configuration of the shells 20, 40, the central body 60, and the sheath 70, are complementary. As such the geometric configuration of these components cooperate to (1) join the components into a unitary structure, and (2) define important functional features of the device.

Preferably, shells 20, 40 are cup-like so as to include an outer convex surface 23 and an inner concave surface 21, 41. The outer surfaces 23 can be coated with a nonspherical sintered bead coating 22, 42, or with some other coating that will promote bony ingrowth. The inner surfaces 21, 41 (shown in FIG. 6) are preferably very smooth, and may be machined or polished.

The shells, 20, 40 include a number of geometric features that as described in further detail below cooperate with other components of the devices. Specifically, these features include a central retaining post 27, 47, an outer circumferential groove 82, 84, and radial stop or an extension 86, 88. The central retaining post 27, 47 extends axially from inner surfaces 21, 41. In addition, each shell 20, 40 includes an edge 73, 74, respectively. The outer circumferential grooves 82, 84 extend into the edges 73, 74 of the shells 20, 40. As seen best in FIG. 6, the radial stops or extensions 86, 88 extend from the edge 73, 74 in a direction generally perpendicular to the general plane of the shells 20, 40.

Each shell may also be provided with tabs or flanges 25, 45. The tabs or flanges extend from a portion of the edge 73, 74 in a direction generally perpendicular to the general plane of the shells 20, 40, but in a direction generally opposite the radial stops or extensions 86, 88. The tabs or flanges 25, 45 help to prevent longterm migration within the disc space, as well as catastrophic posterior expulsion, and the resulting damage to the spinal cord, other nerves, or vascular structures. Insertion stops 25, 45 may contain openings 26, 46 that can releasably engage an insertion tool (not shown). The insertion tool will generally contain flexible prongs to releasably engage openings 26, 46. The insertion tool will also generally include a disengagement block that can press against the side of the implant once it has been properly positioned in the intervertebral space and force the openings 26, 46 off of the prongs of the tool. The shells can be made from any suitable biocompatible rigid material. In accordance with a preferred embodiment, the shells are made from a titanium alloy, and most preferably the titanium alloy is ASTM F-136. The bead coating 22, 42, however, is preferably made from ASTM F-67 pure titanium.

As shown best in FIG. 7, central body 60 is a preferably a donut-shaped structure, and includes a convex upper contact surface 94, a convex lower contact surface 96, and a central axial opening 98. In addition, central body member 60 preferably includes an upper shoulder 92 and a lower shoulder 90. Each shoulder 90, 92 consists of an indentation in the surface of the central body member which defines a ledge that extends around the circumference of the central body 60.

The central body 60 is both deformable and resilient, and is composed of a material that has surface regions that are harder than the interior region. This allows the central body to be sufficiently deformable and resilient that the implant functions effectively to provide resistance to compression and to provide dampening, while still

providing adequate surface durability and wear resistance. In addition, the material of the central body has surfaces that are very lubricious, in order to decrease friction between the central body and the rigid opposing shells.

The material used to make the central body is typically a slightly elastomeric biocompatible polymeric material, which may be coated or impregnated to increase surface hardness, or lubricity, or both, as described above. Coating may be done by any suitable technique, such as dip coating, and the coating solution may include one or more polymers, including those described below for the central body. The coating polymer may be the same as or different from the polymer used to form the central body, and may have a different durometer from that used in the central body. Typical coating thickness is greater than about 1 mil, more particularly from about 2 mil to about 5 mil. Examples of suitable materials include polyurethanes, such as polycarbonates and polyethers, such as Chronothane P 75A or P 55D (P-eth-PU aromatic, CT Biomaterials); Chronoflex C 55D, C 65D, C 80A, or C 93A (PC-PU aromatic, CT Biomaterials); Elast-Eon II 80A (Si-PU aromatic, Elastomedic); Bionate 55D/S or 80A-80A / S (PC-PU aromatic with S-SME, PTG); CarboSil-10 90A (PC-Si-PU aromatic, PTG); Tecothane TT-1055D or TT-1065D (P-eth-PU aromatic, Thermedics); Tecoflex EG-93A (P-eth-PU aliphatic, Thermedics); and Carbothane PC 3585A or PC 3555D (PC-PU aliphatic, Thermedics).

The last main component of this preferred embodiment of the present invention is the sheath 70. As shown in FIG. 7, the sheath 70 is a tubular structure, and is made from a flexible material. The material used to make the sheath is typically biocompatible and elastic, such as a segmented polyurethane, having a thickness ranging from about 5 to about 30 mils, more particularly about 10-11 mils. Examples of suitable materials include BIOSPAN-S (aromatic polyetherurethaneurea

attachment mechanism for inserting the device, and providing a port for the insertion of lubricant into the implant cavity.

The kinematics of the motion provided by the prosthesis are defined primarily by the geometric interaction of the central body 60 and the shells 20, 40. Although the central body is encapsulated within the sheath and the shells, it is not attached to these components. Accordingly, the central body 60 freely moves within enclosed structure and is only constrained by geometric limitations. As seen best in FIG. 6, the concave shape of the inner surfaces 21, 41 of shells 20, 40 complements the convex surfaces 94, 96 of central body 60. As the shells 20, 40 glide across the convex surfaces 94, 96, relatively unconstrained translational, flexural, or extensional motion of shells 20, 40 with respect to central body 60 is achieved. When the desired limit of the range of motion is reached, extensions 86, 88 on shells 20, 40 are designed to contact shoulders 90, 92 on the central body 60. Specifically, the inner portion of the extension forms a circumferential ridge that limits the range of motion of the shells 20, 40 relative to the central body 60 by contacting central body shoulders 90, 92 at the end of the allowable range of motion. In an actual vertebral joint, this occurs at a joint flexion/extension of about $\pm 10^\circ$, at lateral bending of about 11° , and/or at translation of about 2-3 mm.

As explained above, in one embodiment of the invention, the shells are concavo-convex, and their inner surfaces mated and articulated with a convex outer surface of the deformable resilient central body. The implant also contains a sheath or sleeve that is secured to the rims of the shells with retaining rings, and which, together with the inner surfaces of the shells, forms an implant cavity. In a particular aspect of this embodiment, using a coordinate system wherein the geometrical center of the implant is located at the origin, and assigning the x-axis to the anterior (positive) and

posterior (negative) aspect of the implant, the y-axis to the right (positive) and left (negative) aspect of the implant, and the z-axis to the cephalad (positive) and caudal (negative) aspects of the implant, the convex portion of the outer surface and the concave portion of the inner surface of the shells can be described as a quadric surfaces, such that

$$\frac{x^2}{a^2} + \frac{y^2}{b^2} + \frac{z^2}{c^2} = 1$$

where $(\pm a, 0, 0)$, $(0, \pm b, 0)$, and $(0, 0, \pm c)$ represent the x, y, and z intercepts of the surfaces, respectively. Typical magnitudes for a, b, and c are about 11 mm, 30 mm, and 10 mm, respectively.

The implant is symmetrical about the x-y plane, and is intended to be implanted in the right-left center of the disc space, but may or may not be centered in the anterior-posterior direction. In any event, the implant is not allowed to protrude in the posterior direction past the posterior margin of the vertebral body.

As noted above, geometric features also serve to prevent the expulsion of the central body 60. In particular, this is achieved by the geometric interaction of the shells 20, 40 and the central body 60. Shells 20, 40 also contain central retaining posts 27, 47 which extend axially from inner surfaces 21, 41 into a central axial opening 98 in central body 60 and which stop central body 60 from being expelled from the implant during extreme flexion or extension. The diameter of central axial opening 98 is somewhat larger than the diameter of central retaining posts 27, 47. In the coordinate system described above, the central axis of the retaining post is typically coincident with the z-axis, but may move slightly to accommodate various clinical scenarios. The shape of the post may be any quadric surface. However, a truncated tapered elliptical cone is a particularly suitable geometry. Similarly, the

has been assembled into a unitary structure. This means consists of a central axial opening included in the shells 20, 40. Typically, this opening will be provided through central retaining posts 27, 47. By providing access to the interior of the device, sterilization can be done just prior to implantation of the device. Sterilization is preferably accomplished by introducing an ethylene oxide surface sterilant. Caution should be exercised in using irradiation sterilization, as this can result in degradation of the polymeric materials in the sheath or central body, particularly if these include polyurethanes.

After sterilization, the central openings can be sealed using plugs 28, 48. Preferably, only one plug is inserted first. The plug is inserted using insertion tool 100, shown in FIG. 5, and which contains handle 101 and detachable integral plug 28, 48. The tool is designed so that plug 28, 48 detaches from the tool when a predetermined torque has been reached during insertion of the plug. The tool can then be discarded.

After one plug has been inserted to one of the shells, a lubricant 80 is preferably introduced into the interior of the device prior to inserting the second plug. To do this a syringe is used to introduce the lubricant into the remaining central opening, and the implant is slightly compressed to remove some of the excess air. Another insertion tool 100 is then used to insert a plug into that central opening, and thereby completely seal the interior of the device from its exterior environment. In accordance with the preferred embodiment of the present invention the lubricant 80 is saline. However, other lubricants may be used, for example, hyaluronic acid, mineral oil, and the like.

The two shells 20, 40 are virtually identical in shape and composition, however those of skill in the art will understand that it is possible to use shells of

0924268.032202

As described above, the implant is desirably used as an endoprosthesis inserted between two adjacent vertebral bodies. The implant may be introduced using a posterior or anterior approach. For cervical implantation, an anterior approach is preferred. The implanting procedure is carried out after discectomy, as an alternative to spinal fusion. The appropriate size of the implant for a particular patient, determination of the appropriate location of the implant in the intervertebral space, and implantation are all desirably accomplished using precision stereotactic techniques, apparatus, and procedures, such as the techniques and procedures described in copending U.S. Serial No. 09/783,860, Attorney Docket Number 46739/250563, filed on February 13, 2001, the entire contents of which are hereby incorporated by reference. Of course, non-stereotactic techniques can also be used. In either case, discectomy is used to remove degenerated, diseased disc material and to provide access to the intervertebral space. This access is used to remove a portion of the vertebral body using a burr or other appropriate instruments, in order to provide access to the intervertebral space for a transverse milling device of the type described in U.S. Serial No. 08/944,234, the entire contents of which are hereby incorporated by reference. The milling device is used to mill the surfaces of the superior and inferior vertebral bodies that partially define the intervertebral space to create an insertion cavity having surfaces that (a) complement the outer surfaces of the implant and (b) contain exposed cancellous bone. This provides for an appropriate fit of the implant with limited motion during the acute phase of implantation, thereby limiting the opportunity for fibrous tissue formation, and increases the likelihood for bony ingrowth, thereby increasing long-term stability.

The invention has been described above with respect to certain specific embodiments thereof. Those of skill in the art will understand that variations from

these specific embodiments that are within the spirit of the invention will fall within the scope of the appended claims and equivalents thereto.

202209-06242660

WHAT IS CLAIMED IS:

1. A surgical implant suitable for use in a joint between the surfaces of two bones, comprising:

two rigid opposing shells, each having

an outer surface adapted to engage the surfaces of the bones of a joint in such a way that movement of the shell relative to the bone surface is resisted by friction between the outer surface and the surface of the bone;

an inner surface that is smoother than the outer surface; and

an edge between the outer surface and the inner surface;

a deformable, resilient central body disposed between the inner surfaces of the shells comprising an outer surface, at least a portion of which has a shape that complements and articulates with the shape of the inner surface of one or both rigid opposing shells to allow the inner surface of the rigid opposing shell and the outer surface of the central body to move easily with respect to each other within a constrained range of motion, but to resist such movement outside the constrained range of motion.

2. The surgical implant of claim 1, further comprising:

a flexible sheath extending between edges of the opposing shells, having an inner surface that, together with the inner surfaces of the rigid shells, defines a cavity containing the central body.

3. The surgical implant of claim 2, further comprising:

a liquid lubricant, which occupies at least a portion of the cavity.

4. The surgical implant of claim 1, wherein the inner surface of at least one of the rigid opposing shells comprises a motion limiting device disposed thereon.
5. The surgical implant of claim 4, wherein the motion limiting device comprises a bead or ridge formed on the inner surface.
6. The surgical implant of claim 5, wherein the bead or ridge is located at the edge of the shell, and extends toward the central body.
7. The surgical implant of claim 4, wherein the surface of the central body comprises a motion limiting device disposed thereon, and which contacts the motion limiting device of the shell when the implant reaches the end of an acceptable range of motion.
8. The surgical implant of claim 7, wherein the motion limiting device on the central body retainer comprises a ridge that circumscribes the area of the inner surface of the shell that contacts the outer surface of the central body.
9. The surgical implant of claim 4, wherein the motion limiting device comprises a post extending toward the deformable resilient central body, and wherein the outer surface of the central body further comprises at least one opening adapted to receive the post.
10. The surgical implant of claim 1, wherein the edge of at least one of the rigid opposing shells comprises an tab extending axially away from the central body.
11. The surgical implant of claim 10, wherein the tab is adapted to releasably receive a tool for manipulating, inserting or removing the implant.
12. The surgical implant of claim 11, wherein the edges of both rigid opposing shells comprise a tab.
13. The surgical implant of claim 1, wherein the outer surface of each rigid opposing shell is coated with a biocompatible porous coating.

14. The surgical implant of claim 13, wherein the porous coating comprises nonspherical sintered beads of a biocompatible metal or metal alloy.

15. The surgical implant of claim 14, wherein the rigid shell comprises a titanium alloy and wherein the porous coating comprises nonspherical sintered titanium beads.

16. The surgical implant of claim 1, wherein at least one of the rigid opposing shells further comprises a closable passage between its outer surface and its inner surface.

17. The surgical implant of claim 16, wherein the closable passage comprises a hole that is closable by insertion of a correspondingly sized plug.

18. The surgical implant of claim 2, wherein the edge between the outer surface and the inner surface of the rigid opposing shells comprises a circumferential groove adapted to receive a retaining ring.

19. The surgical implant of claim 18, wherein the sheath overlaps the circumferential groove and is held against the edge of the rigid opposing shells by the retaining ring.

20. The surgical implant of claim 9, wherein the implant is a vertebral endoprosthesis.

21. A vertebral endoprosthesis, comprising:

an upper and a lower rigid, opposed, biocompatible shell, each comprising:

an outer, rough surface;

an inner, smooth concave surface; and

an edge between the surfaces;

wherein the inner smooth surface of at least one of the shells comprises a motion limiting device;

a deformable, resilient central body disposed between the inner, smooth concave surfaces of the upper and lower shells, comprising:

a smooth convex upper surface adjacent to the inner smooth concave surface of the upper shell and a smooth convex lower surface adjacent to the inner smooth concave surface of the lower shell;
motion limiting device disposed on at least one of the smooth convex upper and lower surfaces adapted to contact the motion limiting device and limit the relative motion of the shell with respect to the central body.

22. The vertebral endoprosthesis of claim 21, further comprising:

an elastic sheath disposed between the upper and lower shells and external to the central body, comprising an inner surface, an outer surface, an upper edge attached to the upper shell, and a lower edge attached to the lower shell; wherein the inner surface of the sheath and the inner surfaces of the shells define an enclosed cavity.

23. The vertebral endoprosthesis of claim 22, further comprising a lubricant disposed within the enclosed cavity.

24. The vertebral endoprosthesis of claim 21, wherein the motion limiting device on the shell comprises a first ridge disposed on the inner surface of the shell, and the motion limiting device on the central body comprises a shoulder disposed on the surface of the central body.

25. The vertebral endoprosthesis of claim 24, wherein the first ridge comprises an axial extension of at least a portion of the edge of the shell toward the central body, and circumscribes the area of the inner surface that can contact the smooth convex surface of the central body.

26. The vertebral endoprosthesis of claim 24, wherein the shoulder circumscribes the convex surface of the central body.
27. The vertebral endoprosthesis of claim 21, wherein the outer surface of the shell is convex.
28. The vertebral endoprosthesis of claim 21, wherein the outer surface of the shell comprises a porous biocompatible coating.
29. The vertebral endoprosthesis of claim 28, wherein the porous biocompatible coating comprises nonspherical sintered beads of a biocompatible metal.
30. The vertebral endoprosthesis of claim 21, wherein the edge of at least one of the shells comprises a circumferential groove adapted to be overlapped by the sheath and to receive a retaining ring securing the sheath to the shell.
31. The vertebral endoprosthesis of claim 30, further comprising a retaining ring disposed in the circumferential groove, and compressing the edge of the sheath into the groove.
32. The vertebral endoprosthesis of claim 31, wherein the retaining ring comprises a wire or filament of biocompatible material, formed into a ring.
33. The vertebral endoprosthesis of claim 32, wherein the ends of the ring are laser welded.
34. The vertebral endoprosthesis of claim 21, wherein the edge of at least one of the shells comprises an tab extending axially away from the central body.
35. The vertebral endoprosthesis of claim 34, wherein the tab is adapted to releasably engage a tool for manipulating or inserting the endoprosthesis.
36. The vertebral endoprosthesis of claim 35, wherein the tab comprises an opening to releasably receive a retaining prong of the tool.

37. The vertebral endoprosthesis of claim 21, wherein the inner surface of at least one shell comprises a post extending toward the central body, and wherein the outer surface of the central body comprises at least one opening adapted to receive the post.

38. The vertebral endoprosthesis of claim 21, wherein at least one of the shells further comprises a closable passage between its outer surface and its inner surface.

39. The vertebral endoprosthesis of claim 38, wherein the closable passage comprises a hole that is closable by insertion of a correspondingly sized plug.

40. The vertebral endoprosthesis of claim 39, wherein the hole and plug are threaded with complementary threads.

41. A vertebral endoprosthesis, comprising:

an upper and a lower rigid, opposed biocompatible concavo-convex shell, each comprising:

an outer, rough convex surface, comprising a porous coating of a biocompatible material;

an inner concave surface, comprising:

a smooth contact area; and

an axial post extending toward the opposing shell; and

an edge between the surfaces, comprising:

a circumferential groove adapted to receive a retaining ring;

a first ridge circumscribing the contact area of the inner concave surface and extending axially toward the opposing shell;

a tab extending axially away from the opposing shell, and comprising an opening adapted to releasably engage a tool for manipulating, inserting, or removing the endoprosthesis;

a closable passage between the outer surface and the inner surface of the shell;

a deformable, resilient central body disposed between the inner, smooth concave surfaces of the upper and lower shells, comprising:

smooth convex upper and lower surfaces complementary and adjacent to the smooth contact area of the inner surfaces of the respective upper and lower shells;

a shoulder circumscribing each of the smooth convex upper and lower surfaces and adapted to contact the first ridge of the adjacent shell and limit the relative motion of the shell with respect to the central body;

a laterally extending equatorial ridge disposed between the first ridge of the upper concavo-convex shell and the first ridge of the lower concavo-convex shell;

an opening in the upper and lower convex contact surfaces adapted to receive the axial post of the inner surface of each shell;

an elastic sheath disposed between the upper and lower shells and external to the central body, comprising an inner surface, an outer surface, an upper edge attached to the upper shell, and a lower edge attached to the lower shell, wherein the inner surface of the sheath and the inner surfaces of the shells define an enclosed cavity;

an upper retaining ring of a biocompatible material disposed in the circumferential groove in the upper concavo-convex shell and securing the upper edge of the elastic sheath to the shell and a lower retaining ring of a biocompatible material disposed in the circumferential groove of the lower concavo-convex shell and securing the lower edge of the sheath to the shell.

42. The vertebral endoprosthesis of claim 41, further comprising:
a plug of biocompatible material disposed in the closable passages between
the outer surface and inner surface of at least one of the concavo-convex
shells.
43. The vertebral endoprosthesis of claim 42, further comprising:
a lubricant disposed within the implant cavity.
44. The vertebral endoprosthesis of claim 43, wherein a plug is disposed in the
closable passage of each concavo-convex shell.
45. A bone joint implant comprising an encapsulated central body having a central
axial opening therein.
46. The implant of claim 45 wherein the central body has at least one convex
contact surface.
47. The implant of 46 wherein the central body has an upper and a lower convex
contact surface.
48. A bone joint implant comprising a central body positioned between two shells,
wherein the central body has a central axial opening therein.
49. The implant of claim 48 wherein the central body has at least one convex
contact surface.
50. The implant of 49 wherein the central body has an upper and a lower convex
contact surface.
51. A bone joint implant comprising a central body positioned between two shells,
wherein the central body has a shoulder consisting of an indentation extending around
at least a portion of its perimeter.
52. The implant of claim 51 wherein the central body has at least one convex
contact surface.

00004296.032202

53. The implant of claim 52 wherein the central body has an upper and a lower convex contact surface.
54. The implant of claim 51 wherein the central body has an upper shoulder and a lower shoulder.
55. The implant of claim 54 wherein the central body has at least one convex contact surface.
56. A bone joint implant comprising a central body positioned between two shells, wherein the central body has an upper and a lower contact surface, wherein an upper shoulder extends around a portion of the perimeter of the upper contact surface and a lower shoulder extends around a portion of the perimeter of the lower contact surface.
57. The implant of claim 56 wherein the central body has at least one convex contact surface.
58. The implant of claim 57 wherein the central body has an upper and a lower convex contact surface.
59. A bone joint implant comprising an encapsulated central body having an upper and a lower contact surface, wherein an upper shoulder extends around a portion of the perimeter of the upper contact surface and a lower shoulder extends around a portion of the perimeter of the lower contact surface.
60. The implant of claim 59 wherein the central body has at least one convex contact surface.
61. The implant of claim 60 wherein the central body has an upper and a lower convex contact surface.
62. A bone joint implant comprising a central body positioned between two shells, wherein each shell has a smooth inner surface that contacts the central body.
63. The implant of claim 62 wherein the inner surface is shaped to articulate with

09924298.032202

at least a portion of the central body.

64. A bone joint implant comprising a central body positioned between two shells, wherein each shell has a machined or polished inner surface that contacts the central body.

65. The implant of claim 64 wherein the inner surface is shaped to articulate with at least a portion of the central body.

66. A bone joint implant comprising a central body positioned between two shells, wherein at least one shell has an outer surface that is coated to promote bony ingrowth.

67. The implant of claim 66 wherein the coating is formed by vacuum sintering.

68. The implant of claim 66 wherein the coating is wherein the coating is a porous coating.

69. The implant of claim 66 wherein the coating is wherein the coating is a nonspherical sintered bead coating.

70. The implant of claim 66 wherein the coating is wherein the coating is a titanium coating.

71. The implant of claim 70 wherein the titanium coating meets ASTM F-67.

72. A bone joint implant comprising a central body positioned between two shells, wherein at least one shell has a rough outer surface .

73. A bone joint implant comprising a central body positioned between two shells, wherein at least on shell has an outer surface that is coated to provide friction between the outer surface and bone .

74. A bone joint implant comprising a central body and a lubricant encapsulated within a structure having at least one opening for the introduction of the lubricant into the structure.

75. The implant of claim 74 wherein the structure includes two shells and a sleeve extending between the shells, and the opening is included in at least one of the shells.
76. The implant of claim 75 wherein both shells include openings.
77. A bone joint implant comprising a central body positioned between two shells, wherein at least one shell includes an inner surface having a central retaining post extending therefrom and adapted to allow rotation of the shells relative to the central body .
78. The implant of claim 77 wherein the retaining post is substantially centrally located on the inner surface.
79. The implant of claim 77 wherein the inner surface is of a shape that articulates with the shape of at least a portion of the central body.
80. A bone joint implant comprising a central body positioned between two shells, wherein at least one shell has an edge that includes a radial stop extending generally axially from a portion thereof .
81. The implant of claim 80 wherein at least one shell has an edge having an outer circumferential groove therein .
82. The implant of claim 80 wherein the radial stop extends generally axially a distance of less than about 2.5 mm from the edge.
83. The implant of claim 80 wherein the radial stop is adapted to contact a shoulder formed in the central body when translational, flexural, or extensional forces are applied to the implant.
84. The implant of claim 80 wherein at least one shell has an edge that includes a tab extending generally axially from a portion thereof .
85. The implant of claim 84 wherein the radial stop and the tab are on the same shell and they extend from the shell in opposite directions.

86. A bone joint implant comprising a two shells interconnected by a sleeve to form a cavity therein, and a central body having at least one indentation therein positioned within the cavity, wherein at least one of the shells includes a retaining post that extends into the indentation and at least one of the shells includes an opening to allow introduction of a lubricant into the cavity.
87. The implant of claim 86 wherein both shells include openings.
88. The implant of claim 86 wherein the opening is adapted to being sealed with a plug tool having a handle and a detachable integral plug associated therewith.
89. The implant of claim 88 wherein the plug is adapted to detach from the tool when a predetermined torque has been reached during insertion of the plug into the opening.
90. A method of introducing the lubricant into the implant of 86 comprising slightly compressing the implant to remove excess air, and injecting the lubricant into the opening.
91. A method of introducing the lubricant into the implant of claim 87 comprising: (1) sealing one of the openings, (2) slightly compressing the implant to remove excess air, (3) injecting the lubricant into the unsealed opening, and (4) sealing the second opening.
92. The method of claim 91 wherein the openings in the shells are sealed using a seal plug tool having a segment designed to disengage at a predetermined torque.
93. A bone joint implant comprising an elastomeric central body positioned between two shells wherein the central body is impregnated with a surface hardening substance.
94. A bone joint implant comprising an encapsulated elastomeric central body that is impregnated with a surface hardening substance.

95. A bone joint implant comprising an encapsulated central body that is impregnated with a surface lubricity increasing material.
96. A bone joint implant comprising a central body positioned between two shells, wherein the central body is impregnated with a surface lubricity increasing material.
97. A bone joint implant comprising a central body consisting of one or more integral materials such that the central body has a surface region that is harder than an interior region.
98. The implant of claim 97 wherein the central body is positioned between two shells, and the harder surface region interfaces with at least one of the shells.
99. The implant of claim 97 wherein the central body is encapsulated by a structure, and the harder surface region interfaces with at least a portion of that structure.
100. The implant of claim 99 wherein the structure includes two shells and a sleeve extending between the shells, and the harder surface region interfaces with at least a portion of one of the shells.
101. A bone joint implant comprising a central body having a coating thereon wherein the coating material has a different hardness from the material used to form the central body.
102. The implant of claim 101, wherein the coating increases the surface hardness of the central body.
103. A bone joint implant comprising a central body having a coating thereon, wherein the coating increases the surface lubricity of the central body.
104. A bone joint implant comprising a central body positioned between two shells, wherein the central body has a polymer coating thereon.
105. The implant of claim 104 wherein the polymer is selected from the group

surface of the shells can each be described as a quadric surface, such that

$$\frac{x^2}{a^2} + \frac{y^2}{b^2} + \frac{z^2}{c^2} = 1$$

wherein $(\pm a, 0, 0)$, $(0, \pm b, 0)$, and $(0, 0, \pm c)$ represent the x, y, and z intercepts of the surface, respectively, and may be the same or different for the outer and inner surfaces.

- 115. The system of bone joint implants of claim 114 wherein a is about 11 mm.
- 116. The system of bone joint implants of claim 114 wherein b is about 30 mm.
- 117. The system of bone joint implants of claim 114 wherein c is about 10 mm.
- 118. The system of bone joint implants of claim 14 wherein a is about 11 mm, b is about 30 mm, and c is about 10 mm.
- 119. The system of bone joint implants, wherein a, b and c are the same for the outer and inner surfaces.

20220909.002202

ABSTRACT OF THE DISCLOSURE

The invention relates to a surgical implant that provides an artificial diarthroidal-like joint, suitable for use in replacing any joint, but particularly suitable for use as an intervertebral disc endoprosthesis. The invention contains two rigid opposing shells, each having an outer surface adapted to engage the surfaces of the bones of a joint in such a way that the shells are immobilized by friction between their outer surfaces and the surfaces of the bone. These outer surfaces are sufficiently rough that large frictional forces strongly resist any slippage between the outer surface and the bone surfaces in the joint. They may be convex, and when inserted into a milled concavity, are immediately mechanically stable. Desirably, the outer surfaces of the shells are adapted to allow for bony ingrowth, which further stabilizes the shells in place. The inner surfaces of the shells are relatively smooth, and adapted to slide easily across a portion of the outer surface of a central body disposed between the shells. The central body has a shape that cooperates with the shape of the inner surface of the shell so as to provide a range of motion similar to that provided by a healthy joint. A flexible sheath extends between edges of the opposing shells. The inner surface of this sheath, together with the inner surfaces of the rigid shells, defines a cavity encasing the central body. At least a portion of this cavity is filled with a fluid lubricant, further decreasing the frictional force between inner surfaces of the shell and the surface of the central body.